



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problems

FABRIC PANEL S.T.O.P.™

Web Core Microperforated Vinyl Facings

HIGH STYLE



Pure White
#390493



White
#399043



Flannel
#389330



Blueberry
#389334




Crystal Beach
#389332




Rose Mist
#389331


KNIGHTSBRIDGE



Green Mist
#411307




Stone Blue
#411308



Blue White
#411306



Sand Dune
#411305



Robin Egg
#411309

Description:

Total Weight (oz./lin. yd.) 54" width average	12.0
Total Weight (oz./lin. yd.)	8.0
Vinyl Weight (oz./lin. yd.)	5.0
Fabric Weight (oz./lin. yd.)	3.0
Fabric type and count	Polyester Sheeting (22 x 26)
Total average thickness018

Light Reflectance Value (LR Value) is reported as average percent reflectance as measured by ASTM E-97 test method.

Web Core was applied to 1" thick 7PCF rigid acoustical fiberglass on a #4 mounting and tested for noise reduction coefficient. The result was 0.80 NRC.

This pattern satisfactorily passes physical requirements for type I as listed in G.S.A. Federal Specification CCC-W-408A. (Federal Specification CCC-T-191 details test procedures required.)

Fire Resistance:

This pattern meets the requirements of National Fire Protection Association (NFPA)

Class A or 1."

Flame Spread	20
Smoke Developed	65

*Note: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

Stain Resistance:

(ASTM D-1308, METHOD B-24 hour exposure followed by washing with soap and water.) The following staining agents resulted in NO Stain on the material when using the aforementioned test method.

Ethanol	Pencil	Tea	10% Hydrochloric Acid
Vinegar	Mayonnaise	Milk	10% Sodium Hydroxide
Detergent	Bleach	Coca-Cola	Oleic Acid
Lemon Juice	Crayon	Port Wine	10% Ammonia
Coffee	Ketchup		Hydrogen Peroxide

Cleaning Procedures:

Common dirt and stains may be removed from Web Core products by rubbing lightly with a moistened cloth, sponge or stiff bristle brush using a mild soap, detergent or non-abrasive cleanser. It is important that clean water be used on a constant basis and that the material be towel dried.

CAUTION! Strong organic solvents (such as ketones) and harsh abrasive cleaners are not recommended. These materials will cause dulling, discoloration or softening of the vinyl, thus causing permanent damage.