



ACOUSTICAL SURFACES INC.
Sound Solutions for Over 35 Years | Soundproofing | Acoustics | Noise & Vibration Control



Test Report

Selected Tests on Echo Eliminator

Prepared for Manufacturer and Released to:
Acoustical Surfaces, Inc.
123 Columbia Court North
Chaska, MN 55318

R & D Services, Inc.
P.O. Box 2400
Cookeville, Tennessee 38502-2400

Report: RD10266

Reviewed by: *Ronald S. Graves*
Ronald S. Graves
Vice President

April 8, 2010

The test results in this report apply only to the specimens tested. This report shall not be reproduced, except in full, without written approval of R & D Services, Inc. This report must not be used by the Client to claim product endorsement by R & D Services, Inc., NVLAP or any agency of the U.S. Government.



ACOUSTICAL
Sound Solutions for Over 35 Years

SURFACES INC.
Soundproofing | Acoustics | Noise & Vibration Control



Page 2 of 5

Test Report for Resistance to the Growth of Fungi

Report Summary

Material Description: Echo Eliminator
ASTM Test Method: C 1338-08
Project Number: 1175
Specimen Number: 1175100222-8,9
Report Number: RD101835FR
Date of Report: April 8, 2010
Period of Test: March 2-30, 2010
Test Result: Pass
Number of Specimens Observed: 3
Comparative Material: Southern Yellow Pine
Fungi Checked for Viability: Yes
Regular or Extended Test: Regular

Background

The ASTM Standard Specification for many thermal insulations requires a test for the resistance of the insulation to the growth of fungi. Section 10 of C 1497, ASTM C 1338-08, Section 6.6 of ASTM C 1149, or Section 11 of ASTM C 739-08 are commonly used in the case of building materials. Evaluations for fungi growth are based on visual examinations at 40X magnification. The examinations at 40X magnification compare fungal growth on the material being evaluated with the fungal growth on an untreated comparative material that is exposed to the same environment as the test specimens. Both the material being tested and the comparative material are inoculated with a mixed spore suspension containing five specific fungal species to start the test. Since most fungi thrive in a relatively narrow range of temperature and humidity, inoculated specimens and comparative materials are maintained within temperature and relative



humidity ranges specified in the test method for the 28-day growth period. The purpose of the test is to provide an evaluation of the potential for fungal growth present in the insulation material relative to common types of wood used in building construction. The fungal species used in the tests for thermal insulation are listed below.

<i>Aspergillus niger</i>	ATCC 9642
<i>Aspergillus flavus</i>	ATCC 9643
<i>Aspergillus versicolor</i>	ATCC 11730
<i>Penicillium funiculosum</i>	ATCC 11797
<i>Chaetomium globosum</i>	ATCC 6205

A mixed spore suspension is produced from the above five species in accordance with the test method being followed. The viability of each of the five species is verified with each test as required by the test method being used. The ASTM test methods for resistance to fungal growth require a 40X visual comparison of test material and comparative materials 28 days after inoculation. The criteria for a pass/fail result at the end of the 28-day test period depends on the test method being followed.

Test using ASTM C 1338-08

Each of the replicate test specimens shall be determined to have either no fungal growth, fungal growth no greater than the comparative material, or fungal growth greater than the comparative material.

Results

<u>Specimen</u>	<u>Fungal Growth Comparison</u>
1	<u>No growth.</u>
2	<u>No growth.</u>
3	<u>No growth.</u>

The pass/fail result: Pass

Basis for the pass/fail result: Three of three specimens passed.



ACOUSTICAL

Sound Solutions for Over 35 Years

SURFACES INC.

Soundproofing | Acoustics | Noise & Vibration Control

Page 4 of 5

This R&D Services, Inc. test report and the evaluation contained in the report are limited to the material tested. The extent to which the material tested is representative of the product being manufactured is the sole responsibility of the manufacturer. The test results are not purported to predict the performance of the material in a building or installation.

Karen McLalley

Evaluation:

4-8-10

Date:

Ronald S. Steiner

Review:

4-8-10

Date:

References:

ASTM C 1338-08, "Standard test Method for Determining Fungi Resistance of Insulation Materials and Facings", Annual Book of ASTM Standards, Vol. 04.06.

ASTM C 1497, "Standard Specification for Cellulosic Fiber Stabilized Thermal Insulation", 2002 Annual Book of ASTM Standards, Vol. 04.06, pp. 849-852.

MIL-STD-810E, Method 508.4, "Fungus", 14 July 1989.



P.O. Box 2400
Cookeville, Tennessee 38502-2400
Phone: 931-372-8871
Fax: 931-525-3896

Corrosiveness Test Report

Test Number: RD101836CO Date of Test: February 25-March 11, 2010

Specimen Number: 1175100222-8 Date of Manufacture: Unknown

Description of Test Specimen: Echo Eliminator
Conditioned for > 72 hours at 69.8 +/- 3.6°F and 50 +/- 5% RH

Test Method: ASTM C 739-08, Section 9, "Specification for Cellulosic Fiber Loose-Fill Thermal Insulation."

Rendered by Manufacturer and Released to:
Report Prepared For: Acoustical Surfaces, Inc.

Coupon:	Pass / Fail	Comments:
Aluminum:	<u>Pass</u>	<u>No holes or perforations.</u>
Copper:	<u>Pass</u>	<u>No holes or perforations.</u>
Steel:	<u>Pass</u>	<u>No holes or perforations.</u>

Ronald S. Swales
Reviewed By:

4-8-10
Date:

The results in this report apply only to the specimen tested.