



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)

Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

We Identify and **S.T.O.P.** Your Noise Problem

## Encore™

22 oz. 64" / 15 oz. 62" WIDE · 100% POLYESTER  
22 oz. INHERENTLY FLAME RETARDANT / 15 oz. DURABLY FLAME RETARDANT



ENCORE™ 22 oz. / 64" WIDE CABERNET



ENCORE™ 15 oz. / 62" WIDE BLACK



WHITE



BEIGE



ROSETTA



IRIS



PEWTER



CORONA



ICE BLUE



ROYAL BLUE



PROVINCIAL



CYPRESS



CRIMSON



PLUM



CABERNET



ESPRESSO

Continued on next page...



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)

Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

**We Identify and S.T.O.P. Your Noise Problem**

## ENCORE FABRIC SPECIFICATIONS

QUALITY	22 oz. VELOUR	15 oz. VELOUR
<b>COMPOSITION:</b>	100% polyester	100% polyester
<b>WIDTH:</b>	64 (162 cm)	62 (157 cm)
<b>WEIGHT:</b>	22 oz./yd. (625 g/m)	15 oz./yd. (425 g/m)
<b>FINISH:</b>	Inherently Flame Retardant	Durable FR Finish
<b>FLAME TESTING:</b>	UFAC Class 1 NFPA 701 - Small Scale NFPA 701 - Large Scale NFPA 701 - 1996 Version California Administrative Code Title 19 Paragraph 1237.1 City of NY Bulletin No. 44	UFAC Class 1 NFPA 701 - Small Scale NFPA 701 - Large Scale NFPA 701 - 1996 Version California Administrative Code Title 19 Paragraph 1237.1 City of NY Bulletin No. 44
<b>TEAR STRENGTH:</b>		
Trap (ASTM D5587)	Warp - 32 lbs (142 N) Filling - 52 lbs (231 N)	Warp - 16 lbs (71 N) Filling - 13 lbs (58 N)
Tongue (ASTM D2261)	Warp - 5 lbs (23 N) Filling - 12 lbs (53 N)	Warp - 4 lbs (16 N) Filling - 12 lbs (53 N)
<b>TENSILE STRENGTH:</b>		
Grab (ASTM D5034)	Warp - 60 lbs (266 N) Filling - 147 lbs (653 N)	Warp - 64 lbs (284 N) Filling - 66 lbs (293 N)
Strip (ASTM D5055)	Warp - 23 lbs (102 N) Filling - 100 lbs (444 N)	Warp - 36 lbs (160 N) Filling - 40 lbs (178 N)
<b>ABRASION:</b>		
Wyzenbeek (ASTM D3597)	Exceeds 15,000 Double Rubs	Exceeds 15,000 Double Rubs
Martindale (ASTM D4966)	Exceeds 35,000 Cycles	Exceeds 35,000 Cycles
<b>LIGHT FASTNESS:</b>		
(ASTM D3597, Xenon)	40 to 80 hrs (varies by color)	40 to 80 hrs (varies by color)
<b>CROCKING:</b>		
(AATCC 107)	Wet - 3 to 5 (varies by color) Dry - 3 to 5 (varies by color)	Wet - 3 to 5 (varies by color) Dry - 3 to 5 (varies by color)

### CARE AND CLEANING INSTRUCTIONS

1. Regular Care - Vacuum to remove ordinary lint and dust.
2. Spot Cleaning - Most spots and stains can be removed with a damp sponge, cleaning fluids, or dry cleaning powders. None of these methods should cause spotting.
3. General Cleaning - A professional dry cleaning service is recommended for on site cleaning. Supplementary flame testing is recommended after repeated dry cleaning or washings to ensure that the curtain meets local fire codes.

PATENT PENDING