ASI

Title: Light Reflectance Test Results

Product: 1" 3# Echo Eliminator - White and Grey

Application: Wall Mount

Testing Standard: ASTM E1477

Test Date: 4/4/2018

Why this test: This test evaluates the amount of light reflected by the surface of the material.

Test Result Summary: White: 89.960, Grey: 37.639

SPECIMEN IDENTIFICATION	LUMINOUS REFLECTANCE (Y)
1 - 1" 3# Echo Eliminator - White	91.336
2 - 1" 3# Echo Eliminator - White	89.667
3 - 1" 3# Echo Eliminator - White	89.057
4 - 1" 3# Echo Eliminator - White	89.501
5 - 1" 3# Echo Eliminator - White	89.583
6 - 1" 3# Echo Eliminator - White	90.613
Average	89.960

SPECIMEN IDENTIFICATION	LUMINOUS REFLECTANCE (Y)
1 - 1" 3# Echo Eliminator - Gray	39.210
2 - 1" 3# Echo Eliminator - Gray	39.347
3 - 1" 3# Echo Eliminator - Gray	33.791
4 - 1" 3# Echo Eliminator - Gray	38.351
5 - 1" 3# Echo Eliminator - Gray	40.564
6 - 1" 3# Echo Eliminator - Gray	34.573
Average	37.639

Test ID: I2054.01-106-31 R0

ASI TEST RESULT DISCLAIMER

ASI makes every effort to ensure the accuracy and reliability of the information provided. Laboratory testing is conducted by independent testing organizations. ASI does not guarantee that field tests or independent tests will not vary.

© 2018 ASI