

## Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318 (952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: <a href="mailto:sales@acousticalsurfaces.com">sales@acousticalsurfaces.com</a>
Visit our Website: <a href="mailto:www.acousticalsurfaces.com">www.acousticalsurfaces.com</a>

## We Identify and S.T.O.P. Your Noise Problems



P.O. BOX 2400

Cookeville, Tennessee 38502-2400

Phone 931-372-8871 Fax 931-525-3896

## Report of Thermal Test for R Value

Date of Test: <u>July 27, 2000</u> Test Number: <u>N/A</u>

Date of Manufacture: NA R&D Number: 1175000725-1

R&D Test Number RD021134TR

Description of test specimen: R-19 UltraTouch Blue Batt; 5.5" in thick

Report Rendered by Manufacturer for Acoustical Surfaces Inc.

Report prepared for: Manufacturer/Tod Kean

The results in this report were obtained with a heat-flow meter built and operated in accordance with ASTM C 518. The test results in a value for the apparent thermal conductivity of the test specimen, k, in units W/m.K. The thermal resistivity, R-value per inch, in U.S. customary units is the reciprocal of the product of 6.933 and k.

Heat flow meter:Specimen thickness:Specimen density:	24 by 24 5.500 1.20	inches x inches inches lb/ft³
Cold Plate temperature  Hot plate temperature:  Average specimen temperature:	52.56 97.59 75.08	deg F deg F deg F
Apparent thermal conductivity:Thermal resistivity (R-per-inch): Thermal resistance of specimen:	3.403	Btu.in/ft².hr. °F ft².hr. °FBtu.in ft².hr. °FBtu
Notes: Calibration factor used for manual calculation? NA EMF NA  Edge guards or cabinet temperature satisfactory? Yes  Excessive moisture on cold plate? No  Length of time for test (hours)? 18.7		
Reviewed By:	Date:	

This test conforms to ASTM Test Method C 518 except for the report requirements. The report includes summary data but a full complement of data is available upon request.