



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problem



Element Materials Technology
662 Cromwell Avenue
St Paul, MN
55114-1720 USA

P 651 645 3601
F 651 659 7348
T 888 786 7555
info.stpaul@element.com
element.com

EFFECTIVE THERMAL RESISTANCE TESTING OF COAT OF SILENCE

Rendered by Manufacturer
and Released to:
Acoustical Surfaces, Inc.
123 Columbia Court North
Chaska, MN 55318

Date: April 4, 2012
Author: Briana Hinrichs
Report Number: ESP009578P
Client Purchase Order Number: Check

It is our policy to retain components and sample remnants for a minimum of 30 days from the report date, after which time they may be discarded. The data herein represents only the item(s) tested. This report shall not be reproduced, except in full, without prior permission of Element Materials Technology.

EAR Controlled Data: This document contains technical data whose export and re-export/retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval is required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

This project shall be governed exclusively by the General Terms and Conditions of Sale and Performance of Testing Services by Element Materials Technology. In no event shall Element Materials Technology be liable for any consequential, special or indirect loss or any damages above the cost of the work.

-
- Soundproofing Products • Sonex™ Ceiling & Wall Panels • Sound Control Curtains • Equipment Enclosures • Acoustical Baffles & Banners • Solid Wood & Veneer Acoustical Ceiling & Wall Systems
 - Professional Audio Acoustics • Vibration & Damping Control • Fire Retardant Acoustics • Hearing Protection • Moisture & Impact Resistant Products • Floor Impact Noise Reduction
 - Sound Absorbers • Noise Barriers • Fabric Wrapped Wall Panels • Acoustical Foam (Egg Crate) • Acoustical Sealants & Adhesives • Outdoor Noise Control • Assistive Listening Devices
 - OSHA, FDA, ADA Compliance • On-Site Acoustical Analysis • Acoustical Design & Consulting • Large Inventory • Fast Shipment • No Project too Large or Small • Major Credit Cards Accepted



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problem



INTRODUCTION

This report presents the results of Effective Thermal Resistance Tests conducted on a sample of coating material. The testing was authorized by Mr. John Finn on March 28, 2012. The testing and data analysis were completed on April 2, 2012.

The scope of our work was limited to conducting effective thermal resistance tests on the samples submitted and reporting the results.

OBJECTIVE

This testing measures the steady state thermal transmission through a specimen using a heat flow meter apparatus according to ASTM C518-10 "Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus." This method is a comparative method using a standard reference material traceable to NIST to calibrate the heat flow meter apparatus and comparing results to that standard.

CONCLUSIONS

Sample Identification	Effective "R" Value	
	°F·ft ² ·h/Btu	m ² K/W
Coat of Silence	0.41	0.07

SAMPLE IDENTIFICATION

The sample was identified as a coated piece of drywall material measuring 12" x 12" x 3/4" in size. The coating was identified as "Coat of Silence" by the customer.

TEST METHOD

The specimens were allowed to condition at standard laboratory conditions of 72 ± 4°F and 50 ± 5% relative humidity for at least 40 hours prior to testing. The thermal resistance testing was conducted using ASTM Standard C518-10, "Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus" as a procedural guide. The specimens were placed in the heat flow meter in a horizontal position, and steady-state heat flux measurements were made at a mean temperature of approximately 75°F using a hot (top plate) face temperature of approximately 100°F and a cold face (bottom plate) temperature of approximately 50°F. The heat flux is in the downward directions (hot plate to cold plate). Specimen thermal resistance and thermal conductivity were determined by comparing the heat flux measurements of the specimen to measurements made on a known Standard Reference Material. Resistance values obtained from the Heat Flow Meter are best utilized for homogenous specimens.



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problem



TEST METHOD Continued

Test Method	Test Method Title	Deviations from and/or Parameters to Method
ASTM C518-10, Used as a procedural guide as specimens were not homogenous.	Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus	<p>1-Since the specimen was not homogenous the values stated are for Effective Resistivity for the specimen tested and may vary slightly for other specimens based upon the actual composition of each specimen.</p> <p>2-Density was measured by only applies to specific test specimen due to non-homogeneous and slightly irregular shape.</p> <p>3- The test sample was tested along with a Standard Reference Material (SRM). Resistance values are additive, therefore the Thermal Resistance may be calculated from the combination test.</p>

CALIBRATED TEST EQUIPMENT

Honeywell Temp/RH Chart Recorder, S/N 7852 243000007, ID MM190-024, calibrated 8/11/11, due 8/11/12

Netzsch Heat Flow Meter - HFM 436/3/1ER, S/N 606000788, ID PT163-003, calibrated 11/11/11, due 11/11/12

Kanon 18" Calipers (Vernier), S/N 40190, ID MM160-004, calibrated 4/20/11, due 4/20/12

Mettler BB2400 Balance, S/N M18988, ID PT163-019, calibrated 7/12/11, due 7/12/12

STANDARD REFERENCE MATERIAL

NIST SRM 1450c, high density fiberglass

SRM 1453 I

UNCALIBRATED TEST EQUIPMENT

Neslab Chiller, Model RTE-100, S/N 89CML91040-7



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problem



TEST RESULTS

SAMPLE PROPERTIES:	Units	Coat of Silence + SRM 1453 I	SRM 1453 I	Coat of Silence
Thickness	cm	3.273	1.363	1.910
	inches	1.289	0.537	0.752
Density	kg/m ³	755.86	n/a	755.86
	pcf	47.19	n/a	47.19
Mass Change During Conditioning	Initial, g	1379.32	n/a	1379.32
	Prior to test, g	1380.57	n/a	1380.57
	% of cond. mass	0.09	n/a	0.09
Mass Change During Testing	Prior to test, g	1380.57	n/a	1380.57
	After test, g	1379.51	n/a	1379.51
	% of cond. Mass	-0.08	n/a	-0.08
TEST CONDITIONS:				
Temperature Gradient	K/m	850.07	2027.44	850.07
	°F/in	38.87	92.69	38.87
Mean Temperature	°C	24.02	24.17	24.02
	°F	75.24	75.51	75.24
Temperature Range	°C	27.82	27.63	27.82
	°F	50.08	49.73	50.08
Test Time	hr:min:sec	1:27:21	0:10:47	1:27:21
RESULTS:				
Heat Flux	W/m ²	611	718	4106
	Btu/(h·ft ²)	27	32	183
Thermal Conductivity	W/m·K	0.067	0.033	0.264
	Btu·in/(h·ft ² ·°F)	0.466	0.228	1.830
Thermal Conductance	W/m ² ·K	2.056	2.415	13.818
	Btu/(h·ft ² ·°F)	0.362	0.425	2.433
Thermal Resistivity	m ² ·K/W	14.9	30.4	3.8
	°F·ft ² ·h/Btu/in	2.14	4.38	0.55
Thermal Resistance, "R" Value	m ² ·K/W	0.49	0.41	0.07
	°F·ft ² ·h/Btu	2.76	2.35	0.41

Estimated uncertainty is ±5% or less.

Respectfully submitted,

Briana Hinrichs
Testing Technician
Product Evaluation Department

Reviewed By,

William Stegeman
Advanced Materials Manager
Product Evaluation Department
P 651 659 7230