

# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318 (952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: <a href="mailto:sales@acousticalsurfaces.com">sales@acousticalsurfaces.com</a>
Visit our Website: <a href="mailto:www.acousticalsurfaces.com">www.acousticalsurfaces.com</a>

### We Identify and S.T.O.P. Your Noise Problems



## **United States Testing Company, Inc.**

291 FAIRFIELD AVENUE • FAIRFIELD, NEW JERSEY 07004 • 201-576-6252 • Fax: 201-576-8271

**Engineering Services** 

NUMBER: 107025-2

March 8, 1993

CLIENT: Rendered by Manufacturer

and Released to:

Acoustical Surfaces, Inc.

123 Columbia Court North, Suite 201

Chaska, MN 55318

SUBJECT: Flammability

REFERENCE:

United Process, Inc.

#### SAMPLE IDENTIFICATION:

One (1) sample of panels was submitted and identified by the Client as:

VBD-10 (VBD-5)

#### TEST PROCEDURE:

The submitted sample was tested for Surface Flammability in accordance with the procedures specified in ASTM E-162, "Surface Flammability of Materials Using a Radiant Heat Energy Source". All specimens were pre-dried for 24 hours at 140 F and then conditioned to equilibrium at an ambient temperature of 73 F and a relative humidity of 50%. The mounting was such as to expose the coated side to the radiant heat.



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318 (952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: <u>sales@acousticalsurfaces.com</u>
Visit our Website: <u>www.acousticalsurfaces.com</u>

## We Identify and S.T.O.P. Your Noise Problems

NUMBER 107025-2

#### TEST RESULTS:

<u>Sample</u>	Flame Spread <u>Factor, Fs.</u>	Evolution Factor, O	Flame Spread <u>Index, Is.</u>	Total Average Thickness <u>Inches</u>	Exposed Time <u>Seconds</u>
1	1.00	0.88	0.88	0.270	900
2	1.00	0.88	0.88	0.270	900
3	1.00	0.88	0.88	0.270	900
4	1.00	0.88	0.88	0.270	900
Average			1*		

<u>Visual Characteristics:</u> Charring, light smoke.

Page 2

Testing Supervised by:

SIGNED FOR THE COMPANY

BY

Page 1 Steve Caldarola
Of Senior Supervisor
lv Fire Technology

John Lomash Vice President

**SGS** Member of the SGS Group (Société Générale de Surveillance)

Biology • Chemistry • Environmental • Materials • Facilities in Principal Cities

UNITED STATES TESTING COMPANY REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. AND THEY AND THE NAME OF THE UNITED STATES TESTING COMPANY, INC. OR ITS SEALS OR INSIGNIA ARE NOT TO BE USED UNDER ANY CIRCUMSTANCES IN ADVERTISING TO THE GENERAL PUBIC AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME OF UNITED STATES TESTING COMPANY, INC. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. OUR REPORTS APPLY ONLY TO THE STANDARDS OR PROCEDURES IDENTIFIED TO THE TESTS CONDUCTED AND TO THE SAMPLES TESTED AND/OR INSPECTIONS MADE UNLESS OTHERWISE SPECIFIED. THE TEST AND/OR INSPECTION RESULTS ARE NOT INDICATIVE OR REPRESENTATIVE OF THE QUALITIES OF THE LOT FROM WHICH THE SAMPLE WAS TAKEN OR OF THE APPARENTLY IDENTICAL OR SIMILAR SAMPLE PRODUCTS AND NOTHING CONTAINED IN OUR REPORTS SHALL BE DEEMED TO IMPLY OR MEAN THAT UNITED STATES TESTING COMPANY, INC. CONDUCTS ANY QUALITY CONTROL PROGRAM FOR THE CLIENT TO WHOM THE REPORT IS ISSUED. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM F THIRTY DAYS AT WHICH TIME THEY NAT BE SHIPPED BACK TO THE CLIENT.

<sup>\*</sup>Rounded after averaging to the nearest whole number.