



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problems

SONEX Valueline™

Melamine Foam Acoustical Panels



- **Fiber Free**
- **High Performance**
- **Subtle Texture**
- **Lightweight**

MATERIAL: Melamine Acoustical Foam.

PATTERN: Shallow control surface.

FEATURES: High acoustical performance in mid-frequency noise range.

APPLICATIONS: Industrial applications, offices, broadcasting and recording studios for effective reverberation and reflected noise control.

THICKNESS: 1½", 1⅞", 2½".

SIZE 2'x4'.

DENSITY 0.7 lbs./cub. ft.

STANDARD COLORS: White, Grey.

OPTIONAL HPC-COATED COLORS: Black, Light Grey, White, Almond, Medium Grey, Light Blue, Ivory.

CUSTOM COLORS: *Please contact us to discuss custom color options.*

FLAME SPREAD per ASTM E84: Class A. Natural: 5; Painted: 10; HPC-Coated: 15.

SMOKE DENSITY per ASTM E84: Class A. Natural: 50; Painted: 10, HPC-Coated: 150.

INSTALLATION: ASI S.T.O.P. Noise Acoustical Adhesive.

Sound Absorption per ASTM C-423-902							
	125Hz	250Hz	500Hz	1KHz	2KHz	4KHz	NRC
1-1/2 Natural	0.08	0.29	0.73	0.94	0.97	0.89	0.75
1-1/2 Painted	0.06	0.34	0.79	1.02	1.00	0.98	0.80
1-7/8 Natural	0.17	0.55	1.07	1.15	1.08	1.10	0.95
1-7/8 Painted	0.19	0.55	1.17	1.21	1.15	1.13	1.00
2-1/2 Natural	0.19	0.62	1.15	1.21	1.14	1.20	1.05
2-1/2 Painted	0.20	0.66	1.20	1.19	1.12	1.12	1.05

